

Product name: Hidrol H10 (A+B)

Revised on: 18/07/2022

NAME	VALUE
<u>Color</u>	Grey
<u>Form</u>	Cementitious acrylic powder dispersion
<u>Mixing ratio</u>	3 parts by weight 1 part by weight
<u>Mixing time</u>	3 min
<u>Compressive strength</u>	(EN 196-1): 17,50 ± 2,50 N/mm ²
<u>Flexural strength</u>	(EN 196-1): 8,50 ± 1,50 N/mm ²
<u>Adhesion strength</u>	(EN 1542): 2,30 N/mm ²
<u>Water vapor permeability</u>	Sd=0,45 m (EN ISO 7782-2, Class 1 <5m)
<u>Pot life</u>	60 min at +20 C
<u>Bulk density</u>	1,90 kg/lit
<u>Rain</u>	After approx. 4 hr (after application)
<u>Walking</u>	After approx. 24 hr (after application)
<u>Tile fixing</u>	After approx. 24 hr (after application)
<u>Water pressure</u>	After approx. 7 days (after application)
<u>Filling of foundation pit</u>	After approx. 3 days (after application)